

28% Aquaous ammonium compatibility with AFLAS®



Test method Soaked into the fluid at 70°C for 168h & 720h.
Test fluid 28% Aquaous ammonium
Test piece AFLAS® 100H (standard formulation)

Formulation	AFLAS® 100H	100
	MT-Carbon(N990)	30
	TAIC*	5
	Perkadox® 14**	1
	Sodium Stearate	1

(phr)

Cure Conditions Press molded at 170C for 20min
 Post cured at 200C for 4h

Properties (before test)	AFLAS® 100H	FKM (polyol cure)	FKM (peroxide cure)
Tensile strength [MPa]	21.4	14.0	19.1
Tensile Elongation [%]	259	173	290
Hardness [shore-A]	72	86	68

28% Aquaous ammonium compatibility 70 °C for 168 hours	AFLAS® 100H	FKM (polyol cure)	FKM (peroxide cure)
Change of Tensile Strength [%]	-15	decomposition	decomposition
Change of Tensile Elongation [%]	0	decomposition	decomposition
Change in Hardness [points]	-2	decomposition	decomposition
Volume change [%]	0.6	decomposition	decomposition

28% Aquaous ammonium compatibility 70 °C for 720 hours	AFLAS® 100H	FKM (polyol cure)	FKM (peroxide cure)
Change of Tensile Strength [%]	-15	decomposition	decomposition
Change of Tensile Elongation [%]	0	decomposition	decomposition
Change in Hardness [points]	-2	decomposition	decomposition
Volume change [%]	-0.6	decomposition	decomposition

* Triallylisocyanurate

** 1,3-bis(t-butylperoxy)-diisopropylbenzene. Perkadox® is a registered trademark of Akzo Nobel Chemicals B.V.