

## Acetic acid compatibility with AFLAS®



**Test method** Soaked into the fluid at room temperature for 168 hours  
**Test fluid** Acetic acid  
**Test piece** AFLAS® 150P(standard formulation)

<b>Formulation</b>	AFLAS® 150P	100
	MT-Carbon(N990)	30
	TAIC*	5
	Perkadox® 14**	1
	Sodium Stearate	1

(phr)

**Cure Conditions** Press molded at 170C for 20min  
 Post cured at 200C for 4h

Properties (before test)	AFLAS® 150P	FKM (polyol cure)	FKM (peroxide cure)
Tensile strength [MPa]	18	17	24
Tensile Elongation [%]	260	270	370
Hardness [shore-A]	70	73	67

r.t. Acetic acid compatibility r.t. for 168 hours	AFLAS® 150P	FKM (polyol cure)	FKM (peroxide cure)
Change of Tensile Strength [%]	-42	-61	-43
Change of Tensile Elongation [%]	-19	-45	-12
Change in Hardness [points]	-19	-27	-16
Volume change [%]	27	135	32

\* Triallylisocyanurate

\*\* 1,3-bis(t-butylperoxy)-diisopropylbenzene. Perkadox® is a registered trademark of Akzo Nobel Chemicals B.V.